

Ivory 319 General Purpose Epoxy Adhesive

Description

Trowel consistency adhesive for bonding concrete, wood, steel, fibreglass, cement, glass, ceramic, quarry and mosaic tiles, bricks and most building materials.

Benefits

- · Equal volumes.
- · Easy to mix and apply.
- Long pot life.
- · Can be applied to vertical surfaces.
- · Gap filling.
- Non toxic when cured.

Resistance

Resists most common aggressive chemicals, hydrocarbon fuels, oils and solvents and vegetable oils.

Preparation

All surfaces to be clean, dry and sound in accordance with Ivory Surface Preparation specification for substrate to be bonded.

Application

- Using volumes strictly in accordance with the given mixing ratio, place the contents of each container on a clean, flat wooden board.
- Blend together for 5 minutes by means of a flat putty knife.
- Apply by notched trowel or putty knife and immediately bring the surfaces together.
- If the mixed material is left in the container it will become unusable within one hour.

Technical Information

The figures that follow are typical properties achieved in laboratory tests at 20 $^{\circ}$ C and at 50% Relative Humidity.

No of components : 2

Mixing Ratio

Ep/Act by volume : 1:1
Pot life : 1 hour

Cure Time @ 20°C

Touch Dry : 8 hours
Practical Cure : 24 hours
Full Cure : 7 days

Apply by

Notched trowel or Putty knife

Theoretical Coverage : 1m²/ℓ at 1mm
Overcoat Time : 8 hours
Volume Solids : 100%
Compressive Strength : 70mPa
Bond Steel to Steel : 10mPa

Bond Concrete breaks concrete

 Application Temperature
 : 10°C to 35°C

 Service Temperature
 : Wet 40°C

 Dry 60°C

 Thinners
 : Nil

 Cleaner
 : W.S.B.C.

 Shelf Life
 : 12 months

Specification

All surfaces to be prepared and bonded with Ivory 319. General Purpose Epoxy Adhesive all in accordance with manufacturer's detailed instructions.

Health and safety

Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheet available from Flowcrete on request and sent with each delivery.

Flowcrete SA (Pty) Ltd 176 Voortrekker Street Jacobs Durban Kwa Zulu Natal Tel: +27 31 461 3411

Fax: +27 31 461 3475

Flowcrete SA (Pty) Ltd 47 Forge Road Spartan Gauteng

Tel: +27 11 394 1980 Fax: +27 11 394 3003 Flowcrete SA (Pty) Ltd 1A Gabriel place Cnr Gabriel & Main Road Plumstead Cape Town

Tel: +27 21 797 0214 Fax: +27 21 761 6664