

PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

ALLPRIME PLUS

Technical Specifications

Vehicle Type	Modified Poly Vinyl Butyral
Solvent	Iso Propyl Alcohol
Enviro Rating	Flammable
Dilution / Thinning	No more than 10% of Paintcors Etching Thinners for spraying 20% for dipping
Theoretical Spread Rate	Mild steel 10m ² per litre
Apply with	Brush or spay
Drying time	@ 25°C ± 60 minutes per coat
Wash ability	N/A
Elongation	Good
Pigment	Anti-corrosive pigments
Solids Volume	15%
Flexibility	Good
Colour	Black Oxide
Finish	Matt
Storage	Cool, dry place
Over coating	Undercoat and / or top coat of your choice
Packaging	1L, 5L, 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	N/A
Impact Resistance	N/A
Active Ingredient	Zinc Phosphate Anti-Corrosive Pigment
Additional Amount	N/A
Caution	Flammable
Catalyst Ratio	N/A
Recommended Dry Film	15 micron per coat
Freeze Thaw	N/A
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Black Paint