

PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

ENDURACOAT

Technical Specifications

Vehicle Type	Polyurethane Alkyd
Solvent	Turpentine
Enviro Rating	Flammable 3
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	±10m ² per litre
Apply with	Brush, Roller or spray
Drying time	@ 25°C – 3 hours to touch dry
Wash ability	Excellent
Elongation	N/A
Pigment	Pigmented
Solids Volume	45 - 46%
Flexibility	Fair
Colour	Colour of your choice
Finish	Satin
Storage	Cool, dry place. Keep out of reach of children
Over coating	N/A
Packaging	1L, 5L
Guarantee	7 Years
Conditions of Guarantee	Guaranteed on Interior use only Product to be applied to manufacturers specifications
Resistance to Water	Excellent
Resistance to Solvents	Good
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable (see Material Safety Data Sheet)
Catalyst Ratio	N/A
Recommended Dry Film	45um (microns)
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Thixotropic Gel

Note: This product is supplied as a gel and should not be thinned for brush or roller application