

# PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

## ENVIROPRIME

### Technical Specifications

Vehicle Type	Modified Acrylic
Solvent	Water
Enviro Rating	18.5 g/L (Conforms to Greenstar rating for steel priming)
Dilution / Thinning	No more than 10% water for spraying
Theoretical Spread Rate	Primed steel 10m <sup>2</sup> per litre
Apply with	Brush, roller or spay
Drying time	@ 25°C ± 45 minutes per coat
Wash ability	N/A
Elongation	Good
Pigment	Red Oxide
Solids Volume	± 41 %
Flexibility	Good
Colour	Red Oxide
Finish	Matt
Storage	Cool, dry place
Over coating	Undercoat and / or top coat of your choice
Packaging	1L, 5L, 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Good
Resistance to Solvents	N/A
Impact Resistance	N/A
Active Ingredient	Anti-Corrosive additives
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	40 micron per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Red Emulsion Paint

**NOTE: Allow EnviroPrime to dry for 12 hours if overcoating with a solvent based top coat. VOC's are calculated on specific raw materials used in the product which contain VOC's, namely Glycol, Amine and free monomers. EnviroPrime is Zinc Phosphate Free and non-toxic.**

# PAINTCOR

SUPREME QUALITY *Since 1986*

**Paintcor cc**  
Reg No: CK 86/19456/23  
VAT No: 4830119311  
**Members:** G. Williams, G. Adendorff  
W. Williams

**Head office:** 1494 Mailship  
street, Laser Park, Honeydew, 2040  
**Postal Address:** P.O. Box 917,  
Northriding, 2162  
RSA

**Email**  
sales@paintcor.co.za  
**Website**  
www.paintcor.co.za

**Tel:** 011 794 2885  
**Fax no:** 011 794 6955  
**Emergency Numbers**  
+27(0) 79 528 1565  
+27(0) 84 305 5636



**SABS**  
ISO 9001 CERTIFIED

