## PAINTCOR

SUPREME QUALITY Since 1986

2020 Revision

#### **RIPPLETEX**

#### **Technical Specifications**

Vehicle Type Modified Acrylic

Solvent Water

Enviro Rating Conforms to EU 2010 V.O.C. Rules
Dilution / Thinning This product is supplied ready for Use

1. Semi Textured finish: (Application with conventional roller)

Thin with 10% water.

2. Spiky ripple finish: No dilution

3. Rounded Ripple finish: 5% water dependant on ambient

temperature.

Theoretical Spread Rate Ripple Finish (Sponge Roller) ±2-2.5m<sup>2</sup> per litre

Semi-textured Finish (Sheep skin roller) ±3.5 - 4m<sup>2</sup> per litre

Apply with Brush, Sponge or Lamb's wool roller

Drying time @25°C – Touch dry ± 2 hours. Overcoat: ±3 hours

Wash ability Good
Elongation 200%
Pigment Pigmented
Solids Volume ±54%
Flexibility Good

Colour of your choice

Finish Textured

Storage Cool, dry place

Over coating Not necessary, however Paintcor's Elegance for long term

protection.

Packaging 1L, 5L, 20L Guarantee 7 Years

Conditions of Guarantee Product to be applied to manufacturer's specification. Areas

below damp-proof course, boundary walls and structural

defects are not covered by this guarantee.

Resistance to Water Excellent
Resistance to Solvents Fair

Continue on next page...



www.paintcor.co.za

**Email** 

Tel: 011 794 2885

# PAINTCOR

### SUPREME QUALITY Since 1986

Impact ResistanceGoodActive IngredientN/AAdditional AmountN/A

Caution Safe, Non-Toxic, Non-Flammable

Catalyst Ratio N/A

Recommended Dry Film Ripple finish: ±200 microns (1 coat)

Sheep skin: ±70 microns per coat

Freeze Thaw Pass
Accelerated Stability Pass
Accelerated Weathering Pass

Appearance Thick Emulsion Coating

Note: Do not apply RippleTex with a textured roller unless the painters have been trained in rolling ripple. Contact our technical department should you require assistance.

W. Williams

www.paintcor.co.za

Website