

PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

AQUA MATT

Technical Specifications

Vehicle Type	Modified Acrylic Co-polymer
Solvent	Water
Enviro Rating	22.4g/l of VOC (Conforms to E.U 2010 V.O.C rules)
Dilution / Thinning	Supplied ready for use
Apply with	Brush or Roller
Drying time	1 hour @ 25°C @ ± 150µm film thickness
Theoretical Spread Rate	1m ² per litre
Wash ability	Good
Elongation	200%
Pigment	Pigmented white
Solids Volume	± 58%
Flexibility	Good
Colour	Off White
Finish	Matt
Storage	Cool, dry place
Over coating	AquaSeal, Elegance (Silk) or RuvAcryl
Packaging	250ml, 500ml, 1L, 5L, 20L
Guarantee	5- or 10-years dependant on top coat used
Conditions of Guarantee	5 Years when over coated with Paintcor AquaSeal. 10 Years when over coated with Paintcor's Elegance silk or RuvAcryl. Annual inspection to be carried out on both systems with cracking repaired if necessary and over coating of AquaSeal before the 5-year period end.
Resistance to Water	Excellent
Resistance to Solvents	Some solvents
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Total System Dry Film	0.5mm / 500 micron
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass once over coated
Appearance	Viscous White Coating

Note: For best performance follow application instructions.

PAINTCOR

SUPREME QUALITY *Since 1986*

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311
Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sales@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 CERTIFIED

