

PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

SUBTEX

Technical Specifications

Vehicle Type	Styrene Acrylic
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. Rules
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	Ripple Roller (Textured): $\pm 4\text{m}^2$ / litre Sheepskin Roller: $\pm 6\text{m}^2$
Apply with	Brush or roller
Drying time	@ 25°C - 1 hour
Wash ability	N/A
Elongation	Low
Pigment	Pigmented
Viscosity @ 25°C	Ready for use
Solids Volume	$\pm 52\%$
Flexibility	N/A
Colour	White
Finish	Matt
Storage	Cool, dry place.
Over coating	3 hours @ 25°C
Packaging	1L, 5L and 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Good
Resistance to Solvents	N/A
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	80um per coat (Sheepskin Roller) 120um per coat (Ripple Roller)
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Thick white emulsion coating

Note: If SubTex is applied with a Ripple textured roller, new plaster must first be sealed with Paintcor's AcrySeal to prevent mud cracking. Please contact our Technical Department for training on application with a textured roller