PAINTCOR

SUPREME QUALITY Since 1986

2020 Revision

TERRAFIRMA

Technical Specifications

Vehicle Type Modified Pure Acrylic Adhesion Promoted

Solvent Water

Enviro Rating 18.9 grams VOC per litre (Conforms to E.U 2010 VOC rules)

Dilution / Thinning Supplied ready for use

Theoretical Spread Rate ± 8m² per litre

Apply with Brush, Roller or Spray

Drying time Touch Dry: 15minutes @ 25°C

Overcoatable: 1 hour @ 25°C

Cars can be parked on the drive within 12 hours

Wash ability Good
Elongation 100%
Pigment Pigmented
Solids Volume 40%
Flexibility N/A

Colour Available in dark colours and Paintcor standards colours only

Finish Suede

Storage Cool, dry place.

Over coating N/A

Packaging 1L, 5L and 20L

Guarantee N/A
Conditions of Guarantee N/A
Resistance to Water Excellent
Resistance to Solvents Fair
Impact Resistance Good
Active Ingredient N/A
Additional Amount N/A

Caution Non-Flammable but contains Methanol

Catalyst Ratio N/A

Recommended Dry Film 50µm per coat (On a non-porous surface)

Freeze Thaw Pass
Accelerated Stability Pass
Accelerated Weathering Pass

Appearance Emulsion Paint

Note: This product is NOT to be used on power-floated floors, (hot tyres could pull product from the surface), or interior floors where a high degree of clean-ability and chemical resistance is necessary. VOC's are calculated on specific raw materials used in the product which contain VOC's, namely Glycol, Amine and free monomers.



RSA

www.paintcor.co.za

Email

Website

Tel: 011 794 2885

PAINTCOR

SUPREME QUALITY Since 1986

RSA

+27(0) 84 305 5636





