

# PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

## WOODCOAT

### Technical Specifications

Vehicle Type	Linoleic Rich Flexible Long Oil Alkyds
Solvent	Turpentine
Enviro Rating	Flammable
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	10-15m <sup>2</sup> per litre
Apply with	Brush, Roller OR Spray
Drying time	Surface Dry: 1 hour Hard Dry: 6 hours Overcoat : After 12 hours
Wash ability	Excellent
Elongation	Very Good
Pigment	Non Pigmented
Solids Volume	37.5%
Flexibility	Excellent
Colour	Amber Liquid
Finish	N/A
Storage	Cool, dry place. Keep out of reach of children.
Over coating	N/A
Packaging	1L and 5L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Fair
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable (see Material Safety Data sheet)
Catalyst Ratio	N/A
Recommended Dry Film	± 30 microns per coat Apply at least two coats, best results achieved with 3 coats
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass
Appearance	Amber coloured varnish (clear)